



COATED BOARD 2S 170

A woodfree multicoated high gloss art paper for most demanding HSWO printing. The exclusive print evenness and print gloss give outstanding detail and luxurious appearance on images. Excellent runnability, low ink consumption and excellent ink drying ensure high productivity and profit on the most modern presses.

Typical technical values

Substance	170	g/m ²	ISO 536
Caliper	133	µm	ISO 534
Opacity	98,5	%	ISO 2471
D65 Brightness	99	%	D65/10°
CIE Whiteness	122	%	ISO 11475 D65/10°
Gloss Lehmann	70	%	ISO 8254-1
Smoothness PPS 1MPa	0,6	µm	ISO 8791-4
Bulk	0,8	cm ³ /g	ISO 534

Printing method: Heatset web offset

End uses: art books, brochures, catalogues, luxury magazines, covers and wide circulation, advertising material

Shelf life

2 years

Storage

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.

03/2013.



COATED BOARD 2S 150

A woodfree multicoated high gloss art paper for most demanding HSWO printing. The exclusive print evenness and print gloss give outstanding detail and luxurious appearance on images. Excellent runnability, low ink consumption and excellent ink drying ensure high productivity and profit on the most modern presses.

Typical technical values

Substance	150	g/m ²	ISO 536
Caliper	117	µm	ISO 534
Opacity	97,5	%	ISO 2471
D65 Brightness	99	%	D65/10°
CIE Whiteness	122	%	ISO 11475 D65/10°
Gloss Lehmann	70	%	ISO 8254-1
Smoothness PPS 1MPa	0,6	µm	ISO 8791-4
Bulk	0,8	cm ³ /g	ISO 534

Printing method: Heatset web offset

End uses: art books, brochures, catalogues, luxury magazines, covers and wide circulation, advertising material

Shelf life

2 years

Storage

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.
03/2013.



COATED BOARD 2S 130

A woodfree multicoated high gloss art paper for most demanding HSWO printing. The exclusive print evenness and print gloss give outstanding detail and luxurious appearance on images. Excellent runnability, low ink consumption and excellent ink drying ensure high productivity and profit on the most modern presses.

Typical technical values

Substance	130	g/m ²	ISO 536
Caliper	102	µm	ISO 534
Opacity	95,5	%	ISO 2471
D65 Brightness	99	%	D65/10°
CIE Whiteness	122	%	ISO 11475 D65/10°
Gloss Lehmann	70	%	ISO 8254-1
Smoothness PPS 1MPa	0,6	µm	ISO 8791-4
Bulk	0,8	cm ³ /g	ISO 534

Printing method: Heatset web offset

End uses: art books, brochures, catalogues, luxury magazines, covers and wide circulation, advertising material

Shelf life

2 years

Storage

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.
03/2013.



COATED BOARD 2S 100

A woodfree multicoated high gloss art paper for most demanding HSWO printing. The exclusive print evenness and print gloss give outstanding detail and luxurious appearance on images. Excellent runnability, low ink consumption and excellent ink drying ensure high productivity and profit on the most modern presses.

Typical technical values

Substance	100	g/m ²	ISO 536
Caliper	77	µm	ISO 534
Opacity	91,5	%	ISO 2471
D65 Brightness	99	%	D65/10°
CIE Whiteness	122	%	ISO 11475 D65/10°
Gloss Lehmann	66	%	ISO 8254-1
Smoothness PPS 1MPa	0,9	µm	ISO 8791-4
Bulk	0,8	cm ³ /g	ISO 534

Printing method: Heatset web offset

End uses: art books, brochures, catalogues, luxury magazines, covers and wide circulation, advertising material

Shelf life

2 years

Storage

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.

03/2013.